

# Technical Data Sheet

## Topadd® TP-801

### Description

TP-801 are special SAN processing aids. comparing with general acrylic processing aid, It have the higher molecular weight and viscosity, they are designed for cost-saving purpose owing to the balance of cost and performance.

### Advantage

- Excellent fusion promotion , very fast fusion
- Good cost-performance
- Good surface-gloss of finished product
- No affection on Vicat softening points

### Tech Spec

Specification	Unit	Test standard	TP-801
Appearance	--	--	White powder
Bulk density	g/cm <sup>3</sup>	GB/T 1636-2008	0.45±0.10
Sieve residue (40 mesh)	%	GB/T 2916	≤2.0
Volatile content	%	ASTM D5668	≤1.2
Intrinsic viscosity (η)	--	GB/T 16321.1-2008	11.0-12.0

### Application

TP-801 can be used to producing all kinds for rigid pvc products , such as PVC pipes, PVC pipe fitting, PVC foaming products etc.

### Package and Storage

25kg PP woven bag with PE liner or 20kg paper bag with PE liner

Should be stored in dry and ventilated storeroom. This product is non-dangerous.

For other operations, please refer to SDS instructions provided by the manufacturer.

[www.novistagroup.com](http://www.novistagroup.com)

[info@novistagroup.com](mailto:info@novistagroup.com)

+86-536-8206760

---

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Novista Group and its subsidiaries. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.