

Technical Data Sheet

Topadd® 6135

6135 is lower molecular weight than 135A, better processibility, suitable for high-speed extrusion.

Specification:

Items	UNIT	INDEX	Test Method
Chlorine content	%	35±1	ISO 7725
Heat of Fusion	J/g	≤2.0	DSC
Volatile Matter component	%	≤0.4	ISO 1269
Rate of filtration(40 mesh)	%	≥98	--
Shore Hardness A	°	≤58	ISO 7619
Thermal decomposition	°	≥170	--
Bulk density	g/cm ³	≥0.5	--
Tensile strength	Mpa	≥8.0	ISO 37
Elongation at break	%	≥700	ISO 37
Impurity particle	PC/100g	<15	--
Whiteness E457	°	≥80	--

Applications:

PVC door and window profiles, siding, sheet, fence, PVC pipe, electrical conduit etc.



PVC Sheet

PVC Sewer pipe

PVC Fence



PVC Threading Pipe

PVC Foaming products

PVC Bellow Pipe



PVC Profiles

Windows Profile

PVC Siding



Plastic & polymer additives and solution supplier
E:info@novistagroup.com I: www.novistagroup.com

Package and Storage:

25kg polymeric bag; or 500/550kg super sack.

It is not dangerous cargo .You should handle the material according to the instruction described on MSDS.The MSDS is available from sales department once required.Our regular mark is printed on the surface of package in advance .You should inform our sales person in advance If you don't need this or have any special demand for mark.

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Novista Group and its subsidiaries. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.