

## Technical Data Sheet

### Topolymer® CM130A

130A is one chlorinated polyethylene thermoplastic elastomer, which also has excellent low-temperature toughness and processing ability .The processing property with the high dosage of inorganic filler still keep good and the surface of the production will be smooth and exquisite.

#### Tech Specs

Items	UNIT	INDEX	Test Method
Chlorine content	%	30±1	ISO 7725
Heat of Fusion	J/g	≤2.0	DSC
Volatile Matter component	%	≤0.4	ISO 1269
Rate of filtration(40 mesh)	%	≥98	--
Shore Hardness A	°	≤65	ISO 7619
Tensile strength	Mpa	≥8.0	ISO 37
Elongation at break	%	≥700	ISO 37
Mooney Viscosity	ML(121°C	65-75	--
Whiteness E457	°	≥80	--

#### Applications

It is used for magnetic rubber production and also used as modifier for non-polar rubber for example EPDM.

##### **130A+ ferric oxide powder+ additives**

Manufacture magnetic rubber tape of fridge; magnetic board and various rolling magnetic marker.

##### **130A+EPDM+flame retardant +cross linking agent**

Manufacture wire and cable sheath, cross linking modifier EPDM waterproof coiled material.

#### Package and Storage

25kg PP valve bag ;

The product can be stored under appropriate conditions for two years. But please keep products store in a dry ventilated environment (temperature should not exceed 30°C, in low humidity). Inappropriate storage environment may cause agglomeration. Especially at high temperatures & high humidity, it is recommended not to stack more than 30 days long, it may increase agglomeration phenomenon. Agglomeration does not affect the quality and performance, not a quality problem, but agglomeration material is smashed before using .

+86-536-8206760      [info@novistagroup.com](mailto:info@novistagroup.com)      [www.novistagroup.com](http://www.novistagroup.com)

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Novista Group and its subsidiaries. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.