

Technical Data Sheet

Topolymer® CM135B


CM135B with Medium molecular weight and Mooney viscosity between 75 and 85, It show superior mechanical performances and good processibility in processing.

Tech Specs

Items	UNIT	INDEX	Test Method
Chlorine content	%	35±1	ISO 7725
Heat of Fusion	J/g	≤2.0	DSC
Volatile Matter component	%	≤0.4	ISO 1269
Rate of filtration(40 mesh)	%	≥98	--
Shore Hardness A	°	≤57	ISO 7619
Tensile strength	Mpa	≥8.0	ISO 37
Elongation at break	%	≥700	ISO 37
Mooney Viscosity	ML(125°C 1+4)	75-85	--
Whiteness E457	°	≥80	--

Applications

It is widely used for hose, wire/cable and molded products. Not only it can be used as halide rubber solely but also it can be mixed with CR, CSM, NBR, SBR and NR at any proportion.





Plastic & polymer additives and solution supplier

E: info@novistagroup.com | www.novistagroup.com

Package and Storage

25kg PP valve bag ;

The product can be stored under appropriate conditions for two years. But please keep products store in a dry ventilated environment (temperature should not exceed 30°C, in low humidity). Inappropriate storage environment may cause agglomeration. Especially at high temperatures & high humidity, it is recommended not to stack more than 30 days long, it may increase agglomeration phenomenon. Agglomeration does not affect the quality and performance, not a quality problem, but agglomeration material is smashed before using .

+86-536-8206760

info@novistagroup.com

www.novistagroup.com

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Novista Group and its subsidiaries. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.